
Nucleation and growth processes leading to new glass-ceramics in the bismuth borotellurite system: evidences for a chemical demixtion phenomenon

Marine Cholin , Cécile Genevois , Maggy Dutreilh-Colas , Julie Cornette , Pierre Carles ,
Franck Fayon , Sebastien Chenu , Mathieu Allix , Yann Launay , Gaëlle Delaizir ,
Philippe Thomas , Vincent Couderc , and Jean-René Duclere^{*†}

¹Institut de Recherche sur les CERamiques (IRCER) – Institut de Chimie du CNRS : UMR7315,
Université de Limoges, Centre National de la Recherche Scientifique – Centre Européen de la
Céramique, 12 Rue Atlantis, 87068 LIMOGES CEDEX, France

Abstract

In this work, the molar composition 30TeO₂-40B₂O₃-30Bi₂O₃ doped with 0.5Er₂O₃ was specifically investigated. Thanks to a two-step heat-treatment, which combines both nucleation and growth processes, new glass-ceramics containing Bi₂Te₂O₇ crystals were successfully fabricated. Nucleation parameters (*i.e.* an optimal temperature of 405°C maintained for a duration of 2h) were determined via a DSC study. The growth temperature was fixed at 450°C and a minimum time of 45 min at that temperature was necessary to evidence the first signs of crystallization, as testified by X-ray diffraction data. Mechanisms of crystallization were also deeply explored. Through nanoscale observations by Transmission Electron Microscopy, as well as local chemical analysis coupled with Electron Energy Loss Spectroscopy (EELS) analysis, the impact of the growth process was understood. Starting from a homogeneous nucleated glass, the latter provoked a chemical demixtion characterized by the spatial separation of tellurium enriched areas which will further give birth to the crystallization of boron-free Bi₂Te₂O₇ polycrystals, dispersed within a boron-rich residual amorphous matrix. Besides, such nanoscopic investigations were comforted by the macroscopic Scanning Electron Microscopy data, where it was clearly observed that both the density and size of the polycrystalline entities dispersed in the glassy matrix increase with the time of the growth heat treatment. In addition, Raman spectroscopy data revealed that drastic spectral modifications occur for boron oxide structural units during partial crystallization. Such transformations reflect the strong evolution of the coordination number of boron atoms, which switches from ~ 3.1 in the case of the nucleated glass to a value close to 3.9 for the glass-ceramic sample obtained after a heat treatment of 2h at the growth temperature of 450°C. Raman maps were as well recorded on this series of samples (both glass and glass-ceramics), and a Principal Component Analysis conducted on such maps allowed to statistically confirm the local EELS results, *i.e.* the occurrence of the phase separation with the growth process. Boron Nuclear Magnetic Resonance spectroscopy experiments are now planned on the same samples in order to access the same local modifications occurring around boron atoms during partial crystallization, but thanks to another structural probe. Optical transmission measurements showed that transparency quickly drops after 1h of heat

^{*}Speaker

[†]Corresponding author: jean-rene.duclere@unilim.fr

treatment, in agreement with the size of polycrystalline entities found larger than 500 nm. Finally, photoluminescence properties of Er³⁺-doped samples unambiguously indicated that consequential spectral and temporal modifications occur beyond 45 min to 1h of heat treatment, demonstrating the important changes of the rare-earth ions environment with the crystallization, thus in perfect agreement with all the aforementioned data.

Keywords: borotellurites, glass, ceramics, phase separation, chemical demixtion